


Sample Name:
Random Copolymer Poly(styrene-co-methyl methacrylate)

Sample #: **P9128C-SMM Aran**

Structure:




Composition:
PS (mol%) : **82.0**

Mn x 10 ³ PS-co-PMMA	PDI
68.0	1.45

Synthesis Procedure:

Random Copolymer Poly(styrene-co-methyl methacrylate) is prepared by radical polymerization of styrene and methyl methacrylate. The scheme of the reaction is illustrated below:



Characterization:


The polymer was analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The copolymer composition was calculated from ¹H-NMR spectroscopy by comparing the peak area the aromatic protons at 6.66-7.05 ppm with the protons of methyl methacrylate at about 0.8-3.8 ppm that deducts the contribution of the styrene back bone protons.

Solubility:

Random Copolymer Poly(styrene-co-methyl methacrylate) is soluble in CHCl₃, THF, DMF, toluene and precipitated out from methanol.


¹H-NMR Spectrum of the random copolymer:

P9128C-SMM Aran



SEC of the random copolymer:

P9128C-SMM Aran



Size exclusion chromatograph of random copolymer: poly(S-co-MMA):

M_n=68,000, M_w=100,000, M_w/M_n=1.45

Polystyrene content: 82%mol by NMR