


Sample Name:
Random Copolymer Poly(styrene-co-methyl methacrylate)

Sample #: P9128F-SMMAran

Structure:




Composition:

Poly styrene: (mol%) : 54.0

Mn x 10 ³	PDI
PS-co-PMMA	
68.0	1.6

Synthesis Procedure:

Random Copolymer Poly(styrene-co-methyl methacrylate) is prepared by radical polymerization of styrene and methyl methacrylate. The scheme of the reaction is illustrated below:



Characterization:


The polymer was analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The copolymer composition was calculated from ¹H-NMR spectroscopy by comparing the peak area the aromatic protons at 6.66-7.05 ppm with the protons of methyl methacrylate at about 0.8-3.8 ppm that deducts the contribution of the styrene back bone protons.

Solubility:

Random Copolymer Poly(styrene-co-methyl methacrylate) is soluble in CHCl₃, THF, DMF, toluene and precipitated out from methanol.


¹H-NMR Spectrum of the random copolymer:

P9128F-SMMAran



SEC of the random copolymer:

P9128F-SMMAran



Size exclusion chromatograph of random copolymer: poly(S-co-MMA):

M_n=68,000, M_w=105,000, M_w/M_n=1.6

Polystyrene content: 54%mol by NMR