


Sample Name: **Eight-Arm Poly(ethylene oxide)
Hydroxy Pentaerythritol and Solketal Core**

Sample #: **P9673-8EOOH**

Structure:



Composition:

Mn x 10 ³ (total):	10.0
Mn x 10 ³ (of each arm):	1.2
PDI:	1.2

Characterization:

The polymer was characterized by size exclusion chromatography (SEC): Varian liquid chromatograph equipped with UV and refractive detector. SEC columns from Supelco were used with THF containing 2 vol% (Et)₃N as the eluent. The molecular weights were determined using light scattering detector and viscosity detector. The molecular weights and the polydispersity indices were calculated.

An aqueous GPC column from Supelco(G5000 PWXL) was also used with 0.5 M acetic acid and 0.8 M NaNO₃ as the eluent. It was kept at a constant temperature of 50°C. The flow rate was 1.0 ml/min. The column was calibrated with monodisperse poly(ethylene oxide) standards. The molecular weights and the polydispersity index of polyethylene oxide were calculated by using a Visual Basic GPC software.

Purification of the obtained polymer:

Purification of the obtained polymer was carried out rigorously as follows to ensure the removal of the catalyst side product:


1. Dissolved the polymer in de-ionized distilled water to remove the any insoluble organic catalyst side product.
2. Polymer extracted from water with dichloromethane.
3. Polymer solution in dichloromethane was dried over anhydrous sodium sulfate.
4. Solution filtered and than passed through a column packed with basic Al₂O₃.

5. Solution concentrated on rota-evaporator
6. Solution precipitated in cold diethyl ether.
7. Dried under vacuum for 48h at 38 oC.


Solubility:

Polymer is soluble in water, methanol, ethanol.


¹H NMR spectrum of the 8EO core:



¹H NMR spectrum of the polymer :



SEC elugram of the polymer:



Size Exclusion Chromatogram of Core of Six arm
Based on 4EO Mn of 800 and reaction with solketal
P9673-8EOOH

