


Sample Name: Poly(styrene-b-4-vinyl pyridine)

Sample #: P9895P-S4VP (Electronic Grade)

Structure:



Composition:

| | |
|------------------------------------|---|
| $M_n \times 10^3$ S-b-4VP | PDI |
| 280.0-b-130.0 | 1.10 |
| T _g for PS block: 100°C | T _g for 4VP block: not clear |

Synthesis Procedure:

Poly(styrene-b-4-vinyl pyridine) is prepared by living anionic polymerization in THF at -78 °C in the presence of LiCl an additive.

Characterization:

An aliquot of the anionic polystyrene block was terminated before addition of 4VP and analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The Block copolymer composition was then calculated from ¹H-NMR spectroscopy by comparing the peak area of the 2VP proton at 8.2 ppm with the peak area of the aromatic protons of polystyrene at 6.3-7.2 ppm. The composition of the block copolymer can also be determined by titration in acetic acid/HClO₄ using crystal violet indicator. Copolymer PDI is determined by SEC.

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Solubility:


Poly(styrene-b-4 vinylpyridine) is soluble in THF, toluene, and CHCl₃. The diblock copolymer can also be solubilized in methanol, ethanol depending on its composition. The polymer readily precipitates from hexanes, ether and water.

Purification of the obtained polymer was carried out

rigorously as follows to ensure the removal of the catalyst side product:


1. Dissolved the polymer in CHCl₃ and wash with de-ionized distilled water to remove the any soluble organic catalyst side product.
2. Polymer extracted from water with chloroform.
3. Polymer solution in CHCl₃ was dried over anhydrous sodium sulfate.
4. Solution filtered and than passed through a column packed with basic Al₂O₃.
5. Solution concentrated on rota-evaporator
6. Solution precipitated in cold hexane and redissolved in benzene and freeze dried.
7. Final dried under vacuum for 48h at 50°C.

HNMR Spectrum of the Polymer



SEC for the polymer:


P9895-S4VP



- SEC profile in DMF at 30 °C.
Polystyrene, M_n=280,000, Mw: 308,000 PI=1.10
- Block Copolymer PS(280,000)-b-P4VP(130,000), PI=1.10
(composition by titration and by H NMR)

In THF shows micellization

DSC thermogram for the PS block:



References:

- (1). S. K. Varshney, X. F. Zhong and A. Eisenberg *Macromolecules*, **1993**, 26, 701-706.

- (2). Z.Gao, S. K. Varshney, S. Wong, A. Eisenberg
Macromolecules, **1994**, 27, 7923-7927.