


Sample Name:

**Poly(Styrene-b-methyl methacrylate-b-Styrene)
(radical process)**

Sample #: P9992D-SMMAS

Structure:

**Composition:**

$M_n \times 10^3$ (S-b-MMA-S)	PDI
29.0-b-45.0-b-29.0	1.5
Microstructure of PMMA block	S:H:I contents 55:37:8
T_g for PS block: 106 °C	T_g for MMA block: 127 °C

Synthesis Procedure:

Poly(styrene-b-methylmethacrylate-b-styrene) is prepared by controlled process.

Characterization:

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector.



Thermal analysis:

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).


Solubility:

Polymer is soluble in THF, toluene and CHCl_3 . It precipitates from methanol, ethanol, water and hexanes.

HNMR of the initiator:


**HNMR of the Polymer:****SEC of Sample:**

P9992D-SMMAS



Size Exclusion Chromatography of:

- PMMA center block, $M_n=45000$, $PI=1.4$
- SMMAS, the triblock PS(29000)-b-PMMA(45000)-b-PS(29000), $PI=1.5$

DSC thermogram for MMA block:**Reference:**

S.K. Varshney, P. Kesani, N. Agarwal, J. Xin. Zhang, and M. Rafailovich. Synthesis of ABA type thermoplastic elastomers based on Polyacrylates, *Macromolecules*, 1999, 32, 235.