


Sample Name:
Polystyrene-*b*-poly (2-vinyl pyridine)

Sample #: **P40121-S2VP**

Structure:



Composition of PS-*b*-P2VP diblock copolymer:


$M_n \times 10^3$ (g/mol)	PDI
350.0- <i>b</i> -117.0	1.10

Synthesis:

Polystyrene-*b*-poly (2-vinyl pyridine) was prepared by living anionic polymerization in THF at -78°C in the presence of LiCl as an additive.

Characterization: The polymer was characterized by ^1H NMR and SEC.

^1H NMR spectrum of PS-*b*-P2VP:




References:

1. S. K. Varshney, X. F. Zhong and A. Eisenberg *Macromolecules* **1993**, 26, 701–706.
2. Z.Gao, S. K. Varshney, S. Wong, A. Eisenberg *Macromolecules* **1994**, 27, 7923–7927.

SEC elugram of PS-*b*-P2VP:

P40121-S2VP

Conc (mg/mL)	5.5311
dn/dc (mL/g)	0.1600
Method	PS80k August-08-2016-0000.vcm
Solvent	DMF w 0.023M LiBr
Column	PSS



Sample	Mn	Mw	Mp	MwMn	IV
P40121-S2VP_01.vcl	467,996	515,138	529,120	1.101	1.1427