


Sample Name: UV Cleavable (at 350nm)
Poly(ethylene oxide-b-styrene)

Sample #: P40131C-EOSCleav

Structure:



Composition:

Mn x 10 ³ PEO-b-PS	PDI
5.0-b-110.0	1.22

Synthesis Procedure:


The polymer was synthesized by anionic and controlled radical processes.

Characterization:


PEG-Br and final block copolymer were analyzed by size exclusion chromatography (SEC) to obtain the molecular weight of PEG and polydispersity index (PDI) for both PEG and block copolymer. The final block copolymer composition was calculated from ¹H-NMR spectroscopy by comparing the peak area of the ethylene oxide protons at about 3.6 ppm with the aromatic protons of styrene at about 7.0 ppm.

Solubility: Poly(ethylene oxide-b-styrene) is soluble in THF, and chloroform and it precipitates out in hexane or methanol.

¹H NMR Spectrum of the macroinitiator:




¹H-NMR Spectrum of the block copolymer:



SEC of the block copolymer

P40131C-EOS cleav

Conc (mg/mL)	2.5058
dn/dc (mL/g)	0.1500
Method	PS80k August-08-2016-0000.vcm
Solvent	DMF w/0.023M LiBr
Column	PSS



Sample	Mn	Mw	Mp	Mw/Mn	IV
P40131C-01.vcl	114,773	140,161	128,235	1.221	0.7030