

SEC of Sample:


P10869-SOH

Sample Name:

ω -Hydroxy Terminated Polystyrene

Sample #: P10869- SOH

Structure:




Composition:

$M_n \times 10^3$	PDI
2.3	1.10
T_g (°C)	80 °C

Synthesis Procedure:

ω -hydroxy terminated polystyrene was prepared by living anionic polymerization. The scheme of the reaction is illustrated below:



Characterization:


The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector. Polymer functionality was determined by titration with NaOH solution using phenolphthalein as the indicator.

Thermal analysis:

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T_g) has been considered.

Solubility:

Polymer is soluble in toluene, THF, CHCl_3 and can be precipitated in water and cold methanol.



Size Exclusion chromatography of Hydroxy end poly styrene

— Polystyrene, $M_n=2,300$, $M_w=2,500$ PI=1.10

HNMR of the Product:

