


**Sample Name:** Poly (styrene-*b*-methyl methacrylate)  
(PMMA block is predominantly syndiotactic, >78%)

**Sample #:** P40154-SMMA

**Structure:**



**Composition:**

Mn x 10 <sup>3</sup> S-b-MMA	PDI
4.0-31.0	1.04
T <sub>g</sub> for PS block:	103°C
T <sub>g</sub> for PMMA block:	103°C

**Synthesis procedure:**

The polymer was synthesized by anionic polymerization.


**Characterization:**

The molecular weight and polydispersity index of the polymer were determined by size exclusion chromatography (SEC). The ratio between blocks was calculated from <sup>1</sup>H NMR spectrum.

**Solubility:**

Poly (styrene-*b*-methyl methacrylate) is soluble in THF, toluene, dioxane, chloroform; and it precipitates from methanol, ethanol, hexanes, water.


**<sup>1</sup>H NMR spectrum of the polymer:**



**SEC elugram of S Block:**

**P40154-S Block**

Conc (mg/mL)	2.1623
dn/dc (mL/g)	0.1650
Method	PS80k-October192016-0000.vcm
Solvent	DMF w 0.023M LiBr
Column	PSS




Sample	Mn	Mw	Mp	Mw/Mn	IV
P40154-1_01.vdt	4,045	4,240	4,217	1.048	0.0852

**SEC elugram of the Sample:**

**P40154-SMMA**

Conc (mg/mL)	3.7441
dn/dc (mL/g)	0.1100
Method	PS80k-October192016-0000.vcm
Solvent	DMF w 0.023M LiBr
Column	PSS



Sample	Mn	Mw	Mp	Mw/Mn	IV
PP40154-04_01.vdt	35,451	37,041	36,673	1.045	0.3369

**References:**

1. S. K. Varshney, R. Fayt, Ph. Teyssie, and J.P. Hautekeer US Patent 5,264,527 (1993)
2. Ph. Teyssie, Ph. Bayard, R. Jerome, S. K. Varshney, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.

(v. R-01)