


Sample Name: Polylactide

Sample #: P10890C-LA (DL-Form)

Structure:




Composition:

Mn x 10 ³	PDI
122.0	1.8

Purification:

Unreacted monomer was removed by repeated precipitation from CHCl₃ solution to hexane.



Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography.

Solubility:

Polymer is soluble in toluene, THF, CHCl₃ and CH₂Cl₂. The polymer is insoluble in methanol, hexane and ether.

SEC of Homopolymer:

P10890C-LAOCH₃OH (DL form)

