


**Sample Name:****Poly(Styrene-b-methyl methacrylate-b-Styrene)****(radical process ) PMMA : atactic rich**

Sample #: P10897-SMMAS

**Structure:****Composition:**

Mn $\times 10^3$ (S-b-MMA-S)	PDI
1.0-b-60.0-b-1.0	1.45
Microstructure of PMMA block	S:H:I contents 55:37:8
T <sub>g</sub> for PS block: °C	T <sub>g</sub> for MMA block:

**Synthesis Procedure:**

Poly(styrene-b-methylmethacrylate-b-styrene) is prepared by controlled process.

**Characterization:**




The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector.

**Thermal analysis:**

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T<sub>g</sub>).

**Solubility:**

Polymer is soluble in THF, toluene and CHCl<sub>3</sub>. It precipitates from methanol, ethanol, water and hexanes.

**HNMR of the initiator:****SEC of Sample:****P10897-SMMAS**

Size Exclusion Chromatography of:

— PMMA center block, M<sub>n</sub>=60,000, PI=1.3  
S-MMA-S Mn : 1,000-b-60,000-b-1,000 Mw/Mn 1.45

**Reference:**

S.K. Varshney, P. Kesani, N. Agarwal, J. Xin. Zhang, and M. Rafailovich. Synthesis of ABA type thermoplastic elastomers based on Polyacrylates, *Macromolecules*, 1999, 32, 235.