


Sample Name: Poly (2-vinyl naphthalene)

Sample #: P40335-2VN

Structure:




Composition:

Mn x 10 ³	PDI
226.0	1.38

Synthesis Procedure:

Poly (2-vinyl naphthalene) is synthesized by free radical or anionic living polymerization of 2-vinyl naphthalene.

The reaction scheme is as below:




Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) using THF as an eluent. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

SEC elugram of Homopolymer:

P40335-2VN

Concentration (mg/mL)	13.0342
Sample dn/dc (mL/g)	0.2300
Method File	P580K-Nx(2016-6-0000).vcm
Column Set	3x PL 1113.6000
Solvent	THF



Sample	Mn (Da)	Mw (Da)	Mw/Mn	IV (dL/g)	Mp (Da)
P40335-2VN_01.vdt	225,842	311,425	1.379	0.7348	319,644

For the details of the analysis please read our following publication:

Faquan Zeng, Mu Yang, Jianxin Zhang, **Sunil K. Varshney**, "Synthesis and characterization of block copolymers from 2-vinylnaphthalene by anionic polymerization" J. of Polymer Science, Journal of Polymer Science Part A: Polymer Chemistry, 40, 24, 4387-4397 2002.