


**Sample Name:** Poly (styrene-*b*-methyl methacrylate)  
(PMMA block is predominantly syndiotactic, >78%)

**Sample #:** P40589-SMMA

**Structure:**



**Composition:**

Mn x 10 <sup>3</sup> S-b-MMA	PDI
52.0-b-89.00	1.06
T <sub>g</sub> for PS block:	103°C
T <sub>g</sub> for PMMA block:	103°C

**Synthesis procedure:**

The polymer was synthesized by anionic polymerization.


**Characterization:**

The molecular weight and polydispersity index of the polymer were determined by size exclusion chromatography (SEC). The ratio between blocks was calculated from <sup>1</sup>H NMR spectrum.

**Solubility:**

Poly(styrene-*b*-methyl methacrylate) is soluble in THF, toluene, dioxane, chloroform; and it precipitates from methanol, ethanol, hexanes, water.


**<sup>1</sup>H NMR spectrum of the polymer:**



**SEC elugram of the Polymer:**

**P40589-SMMA**

Conc	10.0953
dn/dc	0.1140
Solvent	DMF w 0.023M LiBr
Flow Rate	0.7000
Method	PS80k-May2017-0000.vcm



Sample	MW Number Average	MW Weight Average	MW at Peak	Polydispersity	Intrinsic Viscosity
P40589-SMMA_01.vdt	141,495	150,260	148,684	1.062	0.3526

**References:**

1. S. K. Varshney, R. Fayt, Ph. Teyssie, and J.P. Hautekeer US Patent 5,264,527 (1993)
2. Ph. Teyssie, Ph. Bayard, R. Jerome, S. K. Varshney, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.