


Sample Name: Poly (ethyl methyl siloxane)
disilanol

Sample #: P16265-EtMS

Structure:




Composition:

$M_n \times 10^3$	M_w/M_n
2.0	1.10

Synthesis Procedure:

The polymerization of the cyclic trimer (1,3,5-trimethyl-1,3,5-triethyl cyclotrisiloxane-D3) (monomer synthesized) was initiated with a monofunctional lithium based initiator in a polar / non-polar solvent mixture.




Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co. SEC instrument was calibrated with monodispersed poly dimethylsiloxane polymers.

Solubility:


The product is soluble in Hexane, toluene, benzene, THF, and CHCl_3 .

H NMR spectrum of the sample:



SEC elugram of Homopolymer:

P16265-EtMS



Size Exclusion Chromatography of Poly(ethylmethyl siloxane)
 $M_n=2,000$, $M_w=2,200$, $PI=1.10$