


Sample Name: Poly (t-butyl acrylate)

Sample #: P40882-tBuA

Structure:



Composition:

$M_n \times 10^3$	PDI
286.0	1.4

Synthesis Procedure:

Poly(t-butyl acrylate) is obtained by anionic process.

Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.


Solubility:

Poly(t-butyl acrylate) is soluble in THF, hexanes (low MW), toluene and CHCl_3 . This polymer precipitates from ethanol and methanol containing 10-15% water.

SEC elugram of the Sample:


P40882-tBuA

Concentration (mg/mL)	1.2901
Sample dn/dc (mL/g)	0.0840
Method File	PS80K-4Dec2017-0000.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	M_n (Da)	M_w (Da)	M_w/M_n	IV (dL/g)	M_p (Da)
P40882-tBuA_01.vdt	286,006	403,451	1.411	1.5439	389,054

Thermogram of tBuA:



References:

1. Ph. Teyssie, Ph. Bayard, R. Jerome, **S. K. Varshney**, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
2. R. Fayt, R. Forte, C. Jacobs, R. Jerome, T. Ouhadi, Ph. Teyssie and **S. K. Varshney**, *Macromolecules*, 1987, 20, 1442-1444.
3. Jerome, R. Forte, **S. K. Varshney**, R. Fayt, and Ph. Teyssie, "The Anionic Polymerization of Alkylacrylates: A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanille and A. Guyot Ed., NATO ASI Series C 215, 101 (1987), CA Vol. 108, 12, 094992.
4. Ph. Teyssie, R. Fayt, C. Jacobs, R. Jerome, L. Leemans, and **S. K. Varshney** *Am. Chem. Soc., Polym. Prepr.* 1988, 28, 2, 52-53