


Sample Name: Poly Carbonate (Bisphenol-A carbonate)

Sample #: P41058G-PC

Structure:



Composition:

Mn x 10 ³	Mw/Mn
23.0	1.06


Characterization:

The product was characterized by size exclusion chromatography (SEC) in THF.

SEC elugram of the Sample:

P41058G-PC

Concentration (mg/mL)	2.2726
Sample dn/dc (mL/g)	0.1850
Method File	PS80K-mar5-2018-0002.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	Mn (Da)	Mw (Da)	Mw/Mn	IV (dL/g)	Mp (Da)
P41058G_01.vdt	22,809	24,230	1.062	0.5043	24,650