


Sample Name: Poly Carbonate (Bisphenol-A carbonate)

Sample #: P41058O-PC

Structure:



Composition:

Mn x 10 ³	Mw/Mn
13.0	1.4


Characterization:

The product was characterized by size exclusion chromatography (SEC) using THF as an eluant.

SEC elugram of the Sample:

P41058O-PC

Concentration (mg/mL)	12.2969
Sample dn/dc (mL/g)	0.1850
Method File	PS105K-April 10-0002.vcm
Column Set	3x PL 1113-6300
Solvent	THF



Sample	Mn (Da)	Mw (Da)	Mw/Mn	IV (dL/g)	Mp (Da)
P41058O_01.vdt	13,309	18,873	1.418	0.2170	16,703