


Sample Name: Poly (styrene-b- tert.butylacrylate)

Sample #: P41097-StBuA

Structure:



Composition:

Mn x 10 ³ S-b-tBuA	PDI
89.0-b-20.0	1.08

Synthesis Procedure:

Poly (styrene-b-tert.butyl acrylate) is prepared by living anionic polymerization in THF at -78 °C using sec.BuLi initiator adduct with α-methyl styrene in the presence of LiCl. For further details please see our published articles.¹⁻³


Characterization:

The product was characterized by size exclusion chromatography (SEC) and ¹H NMR.


Solubility:

Poly(styrene-b-tert.butylacrylate) is soluble in THF, toluene, dioxane and CHCl₃.


¹H NMR spectrum of the PS-b-tBuA:



SEC elugram of the PS block:



SEC elugram of the Sample:



References for further information:

1. S. K. Varshney, R. Fayt, Ph. Teyssie, and J.P. Hautekeer US Patent 5,264,527 (1993)
2. Ph. Teyssie, R. Fayt, **S. K. Varshney**, and C. Jacobs Eur. Pat. Appl., Jan 16, 1991 *Eur.Pat.408420*
Patent Assignees- Atochem S.A France. CA. Vol 114, 26, 247998. "Star Block Copolymers based on Acrylates and Methacrylates and their Manufacture process".
3. Ph.Teyssie, R. Fayt, and **S. K. Varshney**, *Eur. Pat. Appl. Dec. 12, 1990. Eur. Pat.402204*
Patent Assignees-Norsolor S.A. France. CA Vol 114, 20, 186314."Catalyst for the the Anionic Living Polymerization (Meth)acrylates".