


Sample Name: Polystyrene

Sample #: P41452-S

Structure:




Composition:

Mn x 10 ³	PDI
1,417.0	1.08
Tg	84 °C

Synthesis Procedure:

Polystyrene is obtained by living anionic polymerization of styrene as illustrated below:



Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatography equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Solubility:


Polystyrene is soluble in DMF, THF, toluene and CHCl_3 . It precipitates from methanol, ethanol, water and hexanes.

SEC elugram of the polymer in THF:

Agilent GPC/SEC Software

P41452-S

Chromatogram Plot



DSC thermogram of the polymer:

Size: 15.3000 mg

