


Sample Name: Poly (dimethyl siloxane), α,ω -bis(silanol)-terminated

Sample #: P41709C-DMS

Structure:



Composition:

Mn	PDI
1.2	1.24

T_m (°C): -42	T_c (°C): -71 T_g (°C): -127 (Lit.)
-----------------	--

Synthesis Procedure:

The polymer was synthesized by anionic polymerization process.

Characterization:


The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography in toluene. SEC was calibrated with well characterized poly dimethyl siloxane polymers.

^1H NMR of the PDMS end functionalized with Carbinol was used to determine molecular weights.

Solubility:

Poly (dimethyl siloxane), α,ω -bis(silanol)-terminated is soluble in hexane, toluene, cyclohexane, THF and chloroform but precipitates from methanol and ethanol.

^1H NMR spectrum of the Sample:



SEC elugram of Homopolymer:

P41709C-DMS-2SIOH

dn/dc	0.1100
Solvent	Toluene
Flow Rate	1.0000
Method	PS100K-July2019-0001.vcm

