


Sample Name: Poly (styrene-co-2-vinyl pyridine), α -hydroxy-terminated

Sample #: P16427B3-S2VPranOH

Structure:




Composition:

Mn x 10 ³ PS-co-P2VP	4.5
PDI	1.3
Styrene: 2VP molar ratio	70:30

Synthesis Procedure:

The polymer is prepared by RAFT polymerization process using RAFT reagent bearing free OH end group.

The following reaction scheme shows how the product was prepared:




Characterization:

The product was characterized by size exclusion chromatography (SEC) and ¹H NMR.


Solubility:

The polymer is soluble in CHCl₃, THF, DMF, toluene and precipitated out from hexane.

NMR spectrum of the RAFT CTA:



¹H-NMR Spectrum of the random copolymer:



SEC elugram of the random copolymer:

Agilent GPC/SEC Software

