


Sample Name: Polystyrene-*block*-poly (2-vinyl pyridine)

Sample #: P42069-S2VP

Structure:



Composition:

Mn x 10 ³ PS-b-2VP	PDI
206.0-b-42.0	1.02

Synthesis Procedure:

Polystyrene-*b*-poly (2-vinyl pyridine) was prepared by living anionic polymerization in THF at -78°C in the presence of LiCl as an additive.


Characterization:

The product was characterized by size exclusion chromatography (SEC) and ¹H NMR.

Solubility:


Poly (styrene-*b*-2 vinylpyridine) is soluble in THF, toluene, and CHCl₃. The diblock copolymer can also be solubilized in methanol, ethanol depending on its composition. The polymer readily precipitates from hexanes, ether and water.

H-NMR Spectrum of the Sample:



SEC elugram of the S block:

Agilent GPC/SEC Software



SEC elugram of the Sample:

Agilent GPC/SEC Software

