


Sample Name: Polystyrene-*block*-poly (2-vinyl pyridine)

Sample #: P42079-S2VP

Structure:



Composition:

Mn x 10 ³ PS-b-2VP	PDI
195.0-b-165.0	1.03

Synthesis Procedure:

Polystyrene-*b*-poly (2-vinyl pyridine) was prepared by living anionic polymerization in THF at -78°C in the presence of LiCl as an additive.


Characterization:

The product was characterized by size exclusion chromatography (SEC) and ¹H NMR.


Solubility:

Poly (styrene-*b*-2 vinylpyridine) is soluble in THF, toluene, and CHCl₃. The diblock copolymer can also be solubilized in methanol, ethanol depending on its composition. The polymer readily precipitates from hexanes, ether and water.

H-NMR Spectrum of the Sample:




SEC elugram of the S block:



Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mz (g/mol)	PD
Peak 1	202734	195113	200699	205116	211629	205289	1.029

SEC elugram of the Sample:

Agilent GPC/SEC Software



Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mz (g/mol)	PD
Peak 1	412263	359540	371145	380847	389038	380704	1.032