

Sample Name:


Poly(methylene-*block*-methyl methacrylate)

Synonym:

Poly(ethylene-*block*-methyl methacrylate)

Sample # P42273A-M-MMA

Structure:



Composition:


$M_n \times 10^3$ (g/mol) [M- <i>b</i> -MMA]	M_w/M_n
4.0- <i>b</i> -25.0	1.14

Thermal properties :

Glass transition temperature, T_g :	85 °C
Melting point, T_m :	126 °C

Synthesis Procedure:

Scheme of polymer synthesis is presented below:



Purification:

The obtained polymer was stirred in hot THF and let it settle down overnight. The soluble fraction was injected to SEC to check any presence of unreacted PMMA. We were unable to detect any signal in SEC in THF.


Characterization:

The product was analyzed using proton NMR, size exclusion chromatography (SEC), and DSC methods.


Solubility:

Polymer is soluble in hot toluene but becomes opaque once solution is cooled down to room temperature.


^1H NMR of the 1st block, allyl-terminated PMMA:




SEC of the 1st block , allyl-terminated PMMA:



^1H NMR of the diblock copolymer in chlorobenzene- d_5 :




GPC of the diblock copolymer in toluene at 60 °C:



DSC of the diblock polymer (2nd heating scan, 10°C/min):

Sample: P42273A_M-MMA
Size: 6.7000 mg

File: P42273A-M-MMA.001



Sample: P42273A_M-MMA
Size: 6.7000 mg

File: P42273A-M-MMA.001

