



Sample Name: Poly(PEG-hexadeca-di-oate); polyester based on poly(ethylene glycol) and hexadecanedioic acid

Sample #: P42379B-EGHDDA

Structure:



SEC profile carried out in THF of Lot# P42379B:



Composition:

$M_n \times 10^3$	Mw/Mn
1.9	1.6
# of PEG average units 2.3	
# of Diacid average units 1.9	
Physical appearance Viscous honey like	

Characterization:

The product was characterized by size exclusion chromatography (SEC) and ^1H NMR.

^1H NMR spectrum of Polymer (400 MHz, DMSO):

