



Polypropylene glycol methyl ether

Structure:




Mn x 10 ³	PDI
2.8	1.15

Polypropylene oxide is synthesized by anionic polymerization of propylene oxide as illustrated in the reaction scheme below.



¹H NMR spectrum of the Polymer in CdCl₃:



P42434E-Run in DMSO

1.00
0.23
1.23

Chromatogram Plot

