

**Poly(methyl methacrylate),  $\alpha$ -hydroxypropyl-terminated**

CAS registry number: 9011-14-7

COC(=O)C(C)(C)[C@@H](Br)CC(C)(C)C(=O)OCCO

$M_n \times 10^3$ (g/mol)	$M_w/M_n$
48.0	1.45

Poly(methyl methacrylate) was obtained by ATRP process.

The molecular weight and polydispersity index of the polymer were determined by size exclusion chromatography (SEC). SEC analysis was performed on Agilent Technologies 1260 Infinity II GPC/SEC system equipped with triple detector, three columns and using tetrahydrofuran (THF) as a mobile phase.

<sup>1</sup>H NMR spectrum of P42622C-MMAOH. The x-axis represents chemical shift in ppm, ranging from 4.2 to 0.6. The spectrum shows several peaks, with the following chemical shifts labeled: 3.77, 3.68, 3.5, 2.9, 2.8, 1.8, 1.7, 1.6, 1.5, 1.4, 1.3, 1.2, 1.15, 1.0, 0.95, and 0.76. The peak at 3.5 ppm is the most intense, followed by the peak at 0.76 ppm.

Molecular Weight Averages							
Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	76664	48096	70135	91014	108697	86938	1.458