


Sample Name:
Poly(methyl methacrylate), α -hydroxypropyl-terminated

Sample #: **P42620-MMAOH**

CAS registry number: 9011-14-7

Structure:



Composition:

$M_n \times 10^3$ (g/mol)	M_w/M_n
146.0	1.5

Synthesis Procedure:

Poly(methyl methacrylate) was obtained by ATRP process.

Characterization:


The molecular weight and polydispersity index of the polymer were determined by size exclusion chromatography (SEC). SEC analysis was performed on Agilent Technologies 1260 Infinity II GPC/SEC system equipped with triple detector, three columns and using tetrahydrofuran (THF) as a mobile phase.

SEC chromatogram of the polymer:

Agilent GPC/SEC Software

P42620

Chromatogram Plot



Molecular Weight Averages

Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	277197	146369	221374	297868	374141	289640	1.512