


Sample Name: Deuterated Polystyrene (d<sub>8</sub>)

Sample #: P42648A-dPS

**Structure:**



**Composition:**

Mn x 10 <sup>3</sup>	PDI
36.5	1.35

**Synthesis Procedure:**

Deuterated polystyrene-d<sub>8</sub> is obtained by free radical polymerization process.


**Characterization:**

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors from Viscotek Co. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used.

**Solubility:**

Deuterated polystyrene-d<sub>8</sub> is soluble in DMF, THF, toluene and CHCl<sub>3</sub>. It precipitates from methanol, ethanol, water and hexanes.

**DNMR spectrum of the Sample:**



**SEC elugram of Homopolymer:**

Agilent GPC/SEC Software

