Product Name: **Poly(2-methyl oxazoline)–*block*–poly(dimethyl siloxane)–*block*–poly(2-methyl oxazoline), with *n*-butyl link between blocks**

Product # **P42686-MEOXZDMSMEOXZ**

Structure:



Composition:

$M_n \times 10^3$ (g/mol) [MEOXZ–*b*–DMS–*b*–MEOXZ]	M_w/M_n
0.8–*b*–3.0–*b*–0.8	1.3

Degree of polymerization (D_p):	10-*b*-40-*b*-10

Synthesis procedure:

The triblock copolymer was synthesized by cationic polymerization technique, using the following linker :



Characterization:

The ratio between blocks was calculated by proton NMR spectroscopy. The molecular weight and polydispersity index were determined by size exclusion chromatography (SEC) by triple analysis method.

^{1}H NMR spectrum of the linker:



^{1}H NMR spectrum of the PDMS-dicarbinol:



^{1}H NMR spectrum of the triblock copolymer:



SEC of PDMS-dicarbinol: