


**Product Name:** Poly(2-methyl oxazoline)-*block*-poly(dimethyl siloxane)-*block*-poly(2-methyl oxazoline), with *n*-butyl link between blocks

**Product #** P42674B-MEOXZDMSMEOXZ

**Structure:**




**Composition:**

$M_n \times 10^3$ (g/mol) [MEOXZ- <i>b</i> -DMS- <i>b</i> -MEOXZ]	$M_w/M_n$
3.0- <i>b</i> -11.0- <i>b</i> -3.0	1.3
Degree of polymerization ( $D_p$ ):	35- <i>b</i> -148- <i>b</i> -35

**Synthesis procedure:**


The triblock copolymer was synthesized by cationic polymerization technique, using the following linker :




**Characterization:**

The ratio between blocks was calculated by proton NMR spectroscopy. The molecular weight and polydispersity index were determined by size exclusion chromatography (SEC) by triple analysis method.


**$^1\text{H}$  NMR spectrum of the linker:**



**$^1\text{H}$  NMR spectrum of the PDMS-dicarbinol:**



**$^1\text{H}$  NMR spectrum of the triblock copolymer:**



**SEC of PDMS-dicarbinol:**

