


Sample Name: Poly (t-butyl acrylate)

Sample #: P42718A-tBuA

Structure:



Composition:

Mn x 10 ³	PDI
17.0	1.10

Synthesis Procedure:

Poly(t-butyl acrylate) is obtained by anionic polymerization process.


Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Solubility:


Poly(t-butyl acrylate) is soluble in THF, DMF and CHCl₃.

SEC elugram of Sample:



Molecular Weight Averages							
Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	19308	17074	18817	20592	22604	20164	1.102

DSC Thermogram of tBuA:



References:

1. Ph. Teyssie, Ph. Bayard, R. Jerome, S. K. Varshney, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
2. R. Fayt, R. Forte, C. Jacobs, R. Jerome, T. Ouhadi, Ph. Teyssie and S. K. Varshney, *Macromolecules*, 1987, 20, 1442-1444.
3. Jerome, R. Forte, S. K. Varshney, R. Fayt, and Ph. Teyssie, "The Anionic Polymerization of Alkylacrylates: A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanaille and A. Guyot Ed., NATO ASI Series C 215, 101 (1987), CA Vol. 108, 12, 094992.
4. Ph. Teyssie, R. Fayt, C. Jacobs, R. Jerome, L. Leemans, and S. K. Varshney *Am. Chem. Soc., Polym. Prepr.* 1988, 28, 2, 52-53