
Sample Name: **Poly (t-butyl acrylate)**

Sample #: **P42718B-tBuA**

Structure:



Composition:


Mn x 10^3	PDI
18.0	1.04

Synthesis Procedure:
Poly(t-butyl acrylate) is obtained by anionic polymerization process.

Characterization:
The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Solubility:
Poly(t-butyl acrylate) is soluble in THF, DMF and CHCl3


SEC elugram of Sample:



Molecular Weight Averages

Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	20086	18310	19089	19767	20397	19672	1.043

DSC Thermogram of tBuA:



References:

1. Ph. Teyssie, Ph. Bayard, R. Jerome, **S. K. Varshney**, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules" 1994, 67.*

2. R. Fayt, R. Forte, C. Jacobs, R. Jerome, T. Ouhadi, Ph. Teyssie and **S. K. Varshney,** *Macromolecules, 1987, 20, 1442-1444.*

3. Jerome, R. Forte, **S. K. Varshney**, R. Fayt, and Ph. Teyssie, "The Anionic Polymerization of Alkylacrylates:A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanaille and A. Guyot Ed., NATO ASI Series *C 215,101 (1987), CA Vol. 108, 12, 094992.*

4. Ph. Teyssie, R. Fayt, C. Jacobs, R. Jerome, L. Leemans, and **S. K. Varshney** *Am. Chem. Soc.,Polym. Prepr. 1988, 28, 2, 52-53*