


Sample Name: Poly(4-vinyl benzoic acid)

Sample #: P43013F-VBA

Structure:



Composition:

Mn x 10 ³	PDI
3.8	1.08
Traces of unreacted monomer	> 0.1%
Presence of unhydrolyzed tert Butyl ester	>1%


Synthesis Procedure: Using cumyl potassium initiator and polymerization at -95 °C.

Poly(4-vinyl benzoic acid) is synthesized by making the 4-t-butyl vinyl Benzoate monomer followed by polymerization and hydrolysis of the t- butoxy group.


Characterization:

The product was characterized by size exclusion chromatography (SEC) and ¹H-NMR data analysis.

¹H-NMR spectrum of Poly 4-Vinyl Benzoic acid:



SEC elugram of Homopolymer:



After Hydrolysis of ester to COOH Mn3,800

FT-IR spectrum:

