


Sample Name:

Poly(dimethylsiloxane), α , ω -bis(silane)-terminated

Sample #: P42774-DMS2SiH

Structure:




Composition:

$M_n \times 10^3$	PDI
7.0	1.3

Synthesis Procedure:

The polymer was prepared by modifying polysiloxane diol using n-butyl lithium as catalyst, followed by dimethylchlorosilane termination. The scheme of the reaction is illustrated below:




Characterization:

The molecular weight and polydispersity index of this polymer was determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector. The modification ratio was calculated from NMR by comparing the silane protons at 4.7ppm and the dimethylsiloxane methyl group at 0.08ppm.

Solubility:


The polymer is soluble in hexane, toluene, cyclohexane, THF and chloroform. It precipitates from methanol and ethanol.

^1H NMR spectrum of the Sample:



SEC elugram of the Sample:

P42774-DMS-2Silane



Size Exclusion Chromatogram of polymer

— PDMS- $M_n=7,000$, $M_w=9,200$, $M_w/M_n=1.3$