


Sample Name: Poly(3-hexylthiophene-2,5-diyl)-b-poly(deuterated methyl methacrylate-d8)

Sample #: P43242A-3HT-d8MMA

Structure:



Composition:

Mn x 10 ³ (3HT-b-d8MMA)	PDI
9.5-b-103.0	2.42

Regioregularity of P3HT: ~90% (H-T)

Purification of polymer:

The crude polymer was recovered from reprecipitation into methanol. The inorganic salts were removed by using a Soxhlet extraction with Methanol and homopoly hexyl thiophene was removed by extraction with hot cyclohexane. The pure polymer was dissolved in chloroform and precipitated in cold Acetone/Hexane.

Characterization:


The product was characterized by size exclusion chromatography (SEC) and ¹H NMR data analysis.

Solubility:

Poly(3-hexyl thiophene-b-MMA-d8) is soluble in THF, Toluene and CHCl₃. It precipitates from methanol and hexane.

H NMR of poly(3-hexylthiophene-b-MMA-d8):

D NMR spectrum of the Sample:



SEC elugram of the polymer:

