


**Sample Name:** Poly(DL-lactide-co-glycolide),  $\alpha$ -acryloxy-terminated

**Sample #:** P43378-DLLAGly-Acrylate

**Structure:**



**Composition:**

$M_n \times 10^3$	PDI
7.0	1.3

DLA: Glycolide Molar ratio 52:48


**Synthetic Procedure:**

The product was synthesized by using 2-Hydroxy ethyl acrylate initiator and Sn Octoate catalyst.


**Characterization:**

The product was characterized by size exclusion chromatography (SEC) and  $^1\text{H}$  NMR data analysis.

**Chemical shifts assignments**



**$^1\text{H}$  NMR spectrum of Random copolymer bearing acryloyl moieties:**



**SEC profile of the polymer:**

