


Sample Name: Poly(styrene-b-ethylene oxide)

Sample #: P43692-SEO

Structure:



Composition:

Mn x 10 ³	PDI
5.0-b-3.0	1.08

Synthesis procedure:

Poly(styrene-b-ethylene oxide) diblock copolymer was prepared by living anionic polymerization.


Characterization:

The product characterized by size exclusion chromatography (SEC) and by ¹H-NMR data analysis.


Solubility:

The polymer is soluble in THF (at 35 °C), CHCl₃, benzene, toluene, dioxane. Low molecular weight SEO with high contents of the polyethylene oxide block can also be solubilized in methanol and water.

¹H NMR spectrum of PS-OH used:




¹H NMR spectrum of PS-PEO (500 MHz, CDCl₃):



SEC elugrams of PS and PS-PEO:

P43692-SEO



Size Exclusion Chromatography:

- Polystyrene, M_n=5,000, M_w=5,500, PI=1.05
- Block Copolymer Polystyrene-b-Poly(ethylene oxide)
- Mw: PS(5,000)-b-PEO(3,000), PI=1.08