


Sample Name: Poly(styrene)-b-poly(N,N-dimethylaminoethyl methacrylate)

Sample #: P41671-SDMAEMA

Structure:



Composition:

Mn x 10 ³ St-b-DMAEMA	Mw/Mn (PDI)
10.5-b-4.5	1.08

Synthesis Procedure:

Poly(styrene-b-N,N-dimethylaminoethyl methacrylate) is prepared by a combination of anionic and RAFT polymerization.


Characterization:

Molecular weight characterization was performed using size-exclusion chromatography (SEC) and ¹HNMR.


Solubility:

Block copolymer soluble in THF, dioxane, CHCl₃. It forms a suspension-like cloudy solution in methanol, ethanol.

SEC profile of the first block:



¹HNMR spectrum of diblock copolymer in CdCl₃:



SEC profile of the block copolymer:

