


Sample Name: Poly (2-Metoxy ethylacrylate)

Sample #: P43778-2MeOEA

Structure:



Composition:

$M_n \times 10^3$	PDI
22.5	1.04


Synthesis Procedure:

The polymer was synthesized by RAFT polymerization process.

Characterization:

The product was characterized by size exclusion chromatography (SEC) and 1H NMR.

1H -NMR spectrum of the Polymer:



SEC elugram of the sample:

