


Sample Name: Poly(1,4-butadiene), ω -hydroxy-terminated

Sample #: P43892-BdOH

Structure:



Composition:

$M_n \times 10^3$	PDI
4.0	1.07

1,4 microstructures: 93%


Synthesis Procedure:

The polymer was synthesized by anionic polymerization process.

Characterization:

The product was characterized by size exclusion chromatography (SEC) and ^1H NMR data analysis.

^1H NMR spectrum of the polymer:



SEC elugram of the polymer:

