


Sample Name: Poly(1,4-butadiene), ω -hydroxy-terminated

Sample #: P43894-BdOH

Structure:



Composition:

Mn x 10 ³	PDI
3.0	1.02

1,4 microstructure: 93%


Synthesis Procedure:

The polymer was synthesized by anionic polymerization process.

Characterization:

The product was characterized by size exclusion chromatography (SEC) and ¹H NMR data analysis.

¹H NMR spectrum of the polymer:



SEC elugram of the polymer:

