


Sample Name: Poly(ethylene oxide)-b-Poly(isopropyl methacrylate)

Sample #: P43936A-EOisoPrMA

Structure:




Composition:

Mn x 10 ³ PEO-b-IsoPrMA	PDI
5.0-b-0.5	1.8

Synthesis Procedure:

Poly(Ethylene oxide- isopropyl methacrylate) is prepared as shown in the scheme below:



Scheme 1. Synthetic route of PEO-b-Poly(isopropyl MA) diblock copolymer


Characterization:

Polymer composition was determined by H NMR taking the integration of PEG block at 3.66 ppm and methyl ester of PMMA block at 3.62 ppm. Molecular weights of the first block and the Mw/Mn of the final and the first block was determined by SEC in THF.

Solubility:

Poly(ethylene oxide -b- isoPrMA) is soluble in CHCl₃, THF, toluene. The polymer precipitated out from hexane.

¹H-NMR Spectrum of the block copolymer:



SEC elugram of the block copolymer:

