


Sample Name: Unsymmetrical
Poly(Styrene-b-methyl methacrylate-b-Styrene)
Triblock copolymer
(Anionic process) PMMA : Syndiotactic rich
Sample #: P11200A-SMMAS
Structure:



Composition:

Mn $\times 10^3$ (S-b-MMA-S)	PDI
88.0-b-325.0-b-15.0	1.28
Microstructure of PMMA block	S:H:I contents 78:10:2
T _g for PS block: Not distinct	T _g for MMA block: 111 °C

Synthesis Procedure:

Poly(styrene-b-methylmethacrylate-b-styrene) is prepared by using anionic and controlled process. You may find details in the published paper: Zhengji Song, Carole Pelletier, Yinghua, Qi, Jasim Ahmed, Sunil K. Varshney, M. A. Jafar Mazumder¹ Synthesis and thermal properties of triblock copolymers of methyl methacrylate using combination of anionic and controlled radical polymerization: Poly(methyl methacrylate) center block bearing different microstructures e-polymer 2012, 067

Characterization:

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector.

Thermal analysis:


Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Solubility:


Polymer is soluble in THF, toluene and CHCl₃. It precipitates from methanol, ethanol, water and hexanes.

NMR of the initiator:


PS-MMA Br diblock copolymer:



PSMMAS triblock:



SEC of Sample:



DSC thermogram for MMA block:

