


Sample Name:

**Poly(N-isopropyl acrylamide), ω-thiol-terminated**

Sample #: **P44473D-NIPAMSH**

Structure:




Composition:

Mv x 10 <sup>3</sup>	PDI
0.9	1.10

Synthesis Procedure:

The polymer was prepared by reversible addition-fragmentation chain transfer polymerization (RAFT) of N-isopropyl acrylamide with AIBN as initiator and cumyl Di thiobenzoate as chain-transfer agent, followed by hydrolysis. The scheme of the reaction is illustrated below:



Purification of polymer:

**Hydrolysis of the Di thiocarbamate End Groups in Poly (NIPAM-SH).** The dithiol end groups of the obtained polymer samples were hydrolyzed to yield the corresponding thiol-terminated polymers under basic conditions. For this purpose, the polymer was dissolved in THF and stirred with excess of isopropyl amine at Room temperature for 24h. Finally, polymer was subjected to sublimation to remove traces amount of NIPAM monomer as observed in its HNMR.

Characterization:

By FTIR, GPC and HNMR

Solubility in different solvents:

THF	✓	DMF	✓
Alcohol	✓	CHCl <sub>3</sub>	✓
Water	X	DMSO	✓

