

# Product Profile


## Identification

**Product Name:** Poly(styrene-b-2-vinyl-pyridine)

**Product Lot Number:** P5744-R-S2VP

**CAS #:** 24980-54-9

**Product Chemical Architecture:**



**Composition:**

<b>Composition (S-b-2VP)</b>	<b>42,500-b-91,500</b>
<b>2VP mole %</b>	<b>68.3</b>
<b>Mn (g/mole)</b>	<b>134,000</b>
<b>Mw (g/mole)</b>	<b>138,000</b>
<b>Mw/Mn</b>	<b>1.03</b>
<b>dn/dc (mL/g) in DMF at 35 °C</b>	<b>0.16</b>

## Method of Synthesis

The polymer is synthesized by anionic polymerization process.

**Solubility in different solvents:**

THF	√	DMF	√
Alcohol	<b>Depends on composition</b>	CHCl <sub>3</sub>	√
Toluene <sub>(hot)</sub>	√	Water	<b>X</b>


## Validation of Architecture

### A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Malvern OmniSec Reveal & Resolve GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LALS 7°) and two columns (PSS, SDV, 8x300 mm). DMF with 0.023M LiBr was the eluent. The flow rate was 0.7 ml/min.

Polymer Source

Malvern Panalytical



Injection Name	RV (mL)	Mn (g/mol)	Mw (g/mol)	Mp (g/mol)	Mz (g/mol)	Mw/Mn
P5744, Injection 1, Peak 1	14.86	134,147	138,315	141,759	143,512	1.031

