

Product Profile

Identification

Product Name: Poly(styrene-b-2-vinyl-pyridine)

Product Lot Number: P9259-R-S2VP

CAS #: 24980-54-9

Product Chemical Architecture:



Composition:

Composition (S-b-2VP)	1,115,000-b-126,000
2VP mole %	10.2
Mn (g/mole)	1,241,000
Mw (g/mole)	1,266,000
Mw/Mn	1.02
dn/dc (mL/g) in DMF at 35 °C	0.16

Method of Synthesis

The polymer is synthesized by anionic polymerization process.

Solubility in different solvents:

THF	√	DMF	√
Alcohol	Depends on composition	CHCl ₃	√
Toluene _(hot)	√	Water	X


Validation of Architecture

A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Malvern OmniSec Reveal & Resolve GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LALS 7°) and two columns (PSS, SDV, 8x300 mm). DMF with 0.023M LiBr was the eluent. The flow rate was 0.7 ml/min.

Polymer Source

Malvern Panalytical



B. NMR (^1H NMR) of S2VP in CHCl_3 (500MHz)

P9259-R
Company Polymer Source
1d_proton_16scans CDCl_3 {D:\Polymer_Source} PSource 52

