

Product Profile

Identification

Product Name: Poly(styrene-b-2-vinyl-pyridine)

Product Lot Number: P10676-R-S2VP

CAS #: 24980-54-9

Product Chemical Architecture:



Composition:

Composition (S-b-2VP)	1,495,000-b-232,000
2VP mole %	13.5
Mn (g/mole)	1,727,000
Mw (g/mole)	1,813,000
Mw/Mn	1.05
dn/dc (mL/g) in DMF at 35 °C	0.16

Method of Synthesis

The polymer is synthesized by anionic polymerization process.

Solubility in different solvents:

THF	√	DMF	√
Alcohol	Depends on composition	CHCl ₃	√
Toluene _(hot)	√	Water	X


Validation of Architecture

A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Malvern OmniSec Reveal & Resolve GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LALS 7°) and two columns (PSS, SDV, 8x300 mm). DMF with 0.023M LiBr was the eluent. The flow rate was 0.7 ml/min.

Polymer Source

Malvern Panalytical



B. NMR (^1H NMR) of S2VP in CHCl_3 (500MHz)

