


Sample Name:

Poly(ethylene oxide-b-6-(4'-cyanobiphenyl-4-yloxy) Propyl methacrylate

Sample #: P11243B-EO4CNBPPPropylMA


Structure:



Composition:

Mn x 10 ³	PDI
PEO-b-4CNBPPPropylMA	
3.0-b-10.6	1.2

Synthesis of Monomer:




Characterization: It was observed SEC columns must have high plate counts to avoid any adsorption with the column packing material. We have used new columns (supelco GHXL 4000 and Water mixed bed column). THF (4% V/V) (Et)₃N as carrier solvent and the polymer solution was prepared in THF with DMF as solvent. (5:5 solution). The SEC carried out at 35 oC column temperature.

Purification of the polymer:



Removal of catalyst: By passing the polymer solution in CHCl₃ through Al₂O₃ (neutral) packed column. The obtained polymer solution was concentrated.

Removal of un-reacted monomer: Polymer was precipitated in hot ethanol-hexane mixture. This steps ensure removal of unreacted monomer which was verified by GPC and by HNMR.


HNMR of the monomer:



HNMR of the PEG-Br used for such synthesis



P11243B-EO4CNBPPPropylMA



Size exclusion chromatography of the product:

— Poly(ethylene oxide), M_n=3,000, M_w=3300, PI=1.09

— Block Copolymer PEO(3,000)-b-4-CNBPPPrMA (10,600), PI=1.20

SEC of the block copolymer:

