

# Product Profile

## Identification

**Product Name:** Poly(styrene-b-2-vinyl-pyridine)

**Product Lot Number:** P19931A-R-S2VP

**CAS #:** 24980-54-9

**Product Chemical Architecture:**



**Composition:**

| Composition (S-b-2VP)        | 461,000-b-38,000 |
|------------------------------|------------------|
| 2VP mole %                   | 7.6              |
| Mn (g/mole)                  | 499,000          |
| Mw (g/mole)                  | 509,000          |
| Mw/Mn                        | 1.02             |
| dn/dc (mL/g) in DMF at 35 °C | 0.164            |

## Method of Synthesis

The polymer is synthesized by anionic polymerization process.


**Solubility in different solvents:**

|                          |                        |                   |   |
|--------------------------|------------------------|-------------------|---|
| THF                      | √                      | DMF               | √ |
| Alcohol                  | Depends on composition | CHCl <sub>3</sub> | √ |
| Toluene <sub>(hot)</sub> | √                      | Water             | X |

## Validation of Architecture

### A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Malvern OmniSec Reveal & Resolve GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LALS 7°) and two columns (PSS, SDV, 8x300 mm). DMF with 0.023M LiBr was the eluent. The flow rate was 0.7 ml/min.



**B.  $^1\text{H}$  NMR of S2VP in  $\text{CDCl}_3$**

